



TECNOPLASTIC C - PLASTIC CHARGES FOR ANTISLIP FINISH

Micronized plastic particles (polyester), designed to texture polyurethane resins, and in this way, achieve surfaces and floorings with an anti-slip finish, in heavy pedestrian traffic situations.

USES

For application in the following situations:

- To mix with polyurethane resins Tecnotop 2C/2CP/1C/S-3000 range of resins to achieve a level of medium-high roughness (depending on the mixing ratio).

NOTE: call our technical department about the application to other substrates or scopes of use

Consumption	5 ~ 8 % depending on the texture desired
Medium size of particle	250 µm (0.250 mm.)



GENERAL SPECIFICATIONS

- It is a coarse powder for producing significant surface texturing. The nature and degree of texturing depend on the applied film thickness and the ratio of texturing agent to binder.
- To mix with Tecnotop range of aliphatic resins
- Conforming even to European norm ENV 12633: (floors slipperiness), to achieve Class 3 (>45 slip resistance), depending on dosage (consult our technical department).
- Depending on the formulation Tecnoplástico C may tend to sediment during storage of the coating. In such cases employing an anti-settling agent is necessary.
- The thermal stability is influenced by the binder and also depends on the duration of exposure. Experiments must be undertaken to precisely determine the thermal stability if long-term exposure to temperatures of more than 140 °C (284°F) is expected.
- It can be used in both solvent-based and solvent-free coatings, and also in water-based coating systems. The areas of application include decorative coatings and anti-slip coatings.
- It is resistant to most customary solvents, but this should be checked when testing the overall coating formulation.

PACKAGING

Metal tins of 2 kg.



STORAGE AND SHELF LIFE

24-months shelf life is stored in original containers in a dry environment at a temperature between 5-35 °C (41-95°F). Keep away from direct sunlight, extreme heat, cold or moisture

MIXING PROCEDURE

Mix the desired dosage in the A component of Tecnotop 2C/2CP/1C/S-3000. The amount to be added in each case will depend on the desired or required texture project, this action can be performed by a speed-stirrer. It does not require the use of added agents, even if water-based systems are used. Perform this action until a homogeneous mixture. In systems containing Pigments texturing agents must be added after grinding these ones

HEALTH AND SAFETY

According to Regulation (EC) No. 1272/2008, Tecnoelastic C is not classified as a dangerous product and therefore does not need to be labeled. Due to the powdery nature of the product, measures for dust protection must be heeded and the build-up of an electrostatic charge must be avoided.

Consult the material and safety data sheet of the product (MSDS).

TECHNICAL AND CHEMICAL PROPERTIES

PROPERTIES	VALUES
Appearance	White powder
Density	±1.28 g/cm ³
Melting range	150-160 °C (302 - 320°F)
Particle size	d50=±320 µm d90=±460 µm

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be used without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

