

PRIMERS RANGE DESIGNED TO MAXIMIZE THE ADHESION IN EVERY SUPPORT

We have developed a range of different resins to maximize grip in any substrate, porous or non-porous, and under different conditions of temperature and humidity as well as to facilitate the implementation of our membranes and floors.



| | PU-1000 | PU-1050 | PUc-1050 | primer EP-1020 |
|--------------------------|------------------------------|-----------------------------|-----------------------------|----------------------|
| Componentes | 1 | 2 | 2 | 2 |
| Product base | Polyurethane solvent base | Polyurethane 100% solids | Polyurethane 100% solids | Epoxi 100% solids |
| For supports | porous | porous | porous | porous |
| Viscosity | 120 cps | 450-A / 900-B cps | 450-A / 900-B cps | 250 cps |
| Initial drying time | 1 hour | 1 hour | 1 hour* | 1 hour |
| Recoat time | 3 ~ 24 hours | 3 ~ 24 hours | 3 ~ 24 hours* | 3 ~ 48 hours |
| Maximum surface humidity | 5 % | 5 % | 5 % | 5 % |

| | primer EP-1040 | primer EPW-1070 | primer | primer-t |
|--------------------------|------------------------|------------------------|----------------------|---------------|
| Componentes | 2 | 2 | 2 | 1 |
| Product base | Epoxi 100% solids | Epoxi water based | Epoxi 100% solids | Alcohol based |
| For supports | porous / non-porous | porous / non-porous | porous | non-porous |
| Viscosity | 850 cps | 3.500 cps | - | 40 cps |
| Initial drying time | 2 hours | 4 ~ 5 hours | 1 hour | 20 minutes |
| Recoat time | 3 ~ 24 hours | 6 ~ 48 hours | 3 ~ 24 hours | - |
| Maximum surface humidity | 15 % | 8 % | 98 % ** | 5 % |



The information on this page has been taken under controlled laboratory conditions (23 ° C / 50% humidity). These data may be modified, always check the updated technical data sheet of the product.

^{*} Data taken at 15°C

^{**} Without negative pressure